

Data Sheet* Advanced-PP 1102 K

Description

Advanced-PP 1102K is a propylene homopolymer for extrusion and thermoforming applications. extremely low water carry-over is a special advantage for the production of raffia tapes.

Applications

Raffia, Thermoformed parts, Tape yarns, monofilament, strapping.

Regulatory Information:

The Grade Advanced-PP 1102K and additives incorporated comply with United States FDA Regulation 21CFR 177.1520 Olefin Polymers and European Regulation (EU) 10/2011 (and its amendments 1282/2011 & 1183/2012). Specific information is available upon request.

Properties (Typical values)

| Properties | Unit | Test method | Value |
|--|---------------------|-------------|-------|
| Melt Flow Rate | | | |
| Melt flow rate (230°C / 2.16 KG) | g / 10 min | ISO 1133 | 3.4 |
| Mechanical Properties | | | |
| Tensile modulus of elasticity (v= 1 mm/min) | MPa | ISO 527-2 | 1500 |
| Tensile stress at yield (v= 50 mm/min) | MPa | ISO 527-2 | 34 |
| Tensile strain at yield (v= 50 mm/min) | % | ISO 527-2 | 9 |
| Tensile strain at break (v= 50 mm/min) | % | ISO 527-2 | >50 |
| Charpy impact strength unnotched (+23°C) | kJ/m ² | ISO 179/1eU | 190 |
| Charpy impact strength notched (+23°C) | kJ/m ² | ISO 179/1eA | 4.0 |
| Ball indentation hardness (H 358/30) | MPa | ISO 2039-1 | 74 |
| Thermal Properties | | | |
| Melting point, DSC | °C | ISO 3146 | 163 |
| Heat deflection temperature ----- HDT/B (0.45 Mpa) | °C | ISO 75-2 | 85 |
| Vicat softening temperature ----- VST/A50 (10 N) | °C | ISO 306 | 154 |
| Other Properties | | | |
| Density | g / cm ³ | ISO 1183 | 0.91 |

* Provisional

Values given here are typical and should not be interpreted as specification. In a view of many factors that may affects processing and application, these data do not relieve the receiver to this information from the responsibility of carry out their own test and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for specific purpose of the product made with or on the basis of the information in this publication.